


25



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 0 735 053 B1**

(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention
of the grant of the patent:
20.10.1999 Bulletin 1999/42

(51) Int Cl.⁶: C08F 6/00, C08F 10/00

(21) Application number: 96104559.8

(22) Date of filing: 22.03.1996

(54) **Removal of oligomers from substantially crystalline, alpha-olefin polymers**

Entfernung von Oligomeren aus im wesentlichen kristallinen Alpha-Olefinpolymeren

Elimination d'oligomères dans des polymères alpha-oléfiniques essentiellement cristallins

(84) Designated Contracting States:
BE DE ES FI FR GB IT NL SE

(30) Priority: 31.03.1995 US 414870

(43) Date of publication of application:
02.10.1996 Bulletin 1996/40

(73) Proprietor: MONTELL NORTH AMERICA INC.
Wilmington Delaware 19850-5439 (US)

(72) Inventors:
• Williams, Stephen D.
Newark, Delaware 19711 (US)

• Fezza, Richard J.
Wilmington, Delaware (US)

(74) Representative:
Luderschmidt, Schüler & Partner GbR
Patentanwälte,
Postfach 3929
65029 Wiesbaden (DE)

(56) References cited:
EP-A- 0 068 146 GB-A- 1 272 778
US-A- 4 314 053

EP 0 735 053 B1

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

[0001] This invention relates to synthetic resins. More particularly, it relates to α -olefin polymers, and the treatment of them to remove undesirable components such as those that occur in their formation.

[0002] As is well known, α -olefin polymers are made by effecting with catalysts the polymerization of α -olefin under time, temperature and pressure conditions selected to result in polymeric products having desired properties. The intended product in each case, most times simply referred to as polymer, is a blend of molecular strands or chains of α -olefin units, which chains have many different chain lengths. While the lengths of most of the chains represent thousands of carbon atoms, inevitably there are chains of much shorter lengths, which can be as low as two α -olefin units, and as high as forty-five or more α -olefin units. These shorter chain length molecules are referred to as oligomers. In the polymerization reaction, oligomers also are formed apart from the intended polymer. To the extent they do not become part of the intended polymer particles, they usually are separated from the polymer particles in an unreacted α -olefin(s) removal procedure generally performed after the polymerization step or steps. Oligomers also can be formed in a polymer as the result of post-polymerization treatments such as, for example, visbreaking, including melt extrusion.

[0003] In most commercial α -olefin polymers, the concentration of oligomers in the polymer particles is not enough to cause a problem. Indeed, the presence of oligomers can have a beneficial effect on the melt rheology of the polymers. However, especially in the case of substantially crystalline, propylene polymers with high melt flow rates (>5 dg/min, ASTM D 1238, Condition L) in which the oligomer concentration is frequently in the range of 1000-10,000 parts per million parts by weight of the polymer, a substantial concentration of oligomers in the polymer causes the emission of "smoke" from the polymer when it is melt extruded as when it is being converted into a useful article. See, for example, the U.S. Patent 4,233,429 to Hoerauf et al. which discloses a method and a device for capturing and removing from the work area volatiles evolved from the molten polymer as it emerges from the extruder die. However, not all of the oligomers evolve from the molten polymer after it leaves the die and before it is cooled to the temperature at which it solidifies. The residual oligomers in the extruded polymer can result in objectionable taste and odor in articles (for example, packaging film and containers of such extruded polymer).

[0004] One method that has been disclosed for reducing the oligomer concentration of a polymer has been to melt the polymer particles and then pass through the melt a liquid or gas in which the oligomers are soluble but the polymer is insoluble. Examples of this method are disclosed in the U.S. Patent 5,200,486 to Beckermeier et al., and the U.S. Patent 5,237,048 to Miyakawa. A major disadvantage of this method is that the resulting purified polymer has a heat history; that is, it has some thermal degradation and changes in physical properties. Such become magnified when the polymer is subjected to further melt procedures such as melt compounding to make resin products, and injection molding, thermoforming, melt spinning and melt casting to make useful articles.

[0005] Consequently, the basic problem to which this invention provides a solution is how to remove undesired oligomers from an α -olefin polymer without melting it.

[0006] The U.S. Patent 4,365,057 to Saito et al. discloses a method for "drying" an α -olefin polymer that has been in a slurry with a 6 to 7 carbon atom hydrocarbon medium, and, after being separated from the slurry, has been treated (as by being contacted with heated nitrogen gas in a conventional dryer such as a fluidized bed dryer) to reduce the concentration of the residual hydrocarbon medium to 0.2-2% by weight. According to the patent, a slurry of this kind can result when the polymer has been formed in such hydrocarbon medium, when it is subjected to catalyst deactivation with an alcohol in such hydrocarbon medium, and when it is treated with such hydrocarbon medium to remove an atactic fraction. The method involves introducing the polymer into the upper part of a silo, introducing nitrogen gas with a dew point of -10°C or lower into the lower part of the silo, discharging polymer, which, the patent emphasizes, descends by gravity within the silo, from the lower part of the silo, and discharging from the upper part of the silo nitrogen gas containing hydrocarbon medium. The drying is carried out at a temperature of $70-130^{\circ}\text{C}$, the retention time of the polymer in the silo is 0.5-20 hours, and the amount of nitrogen gas introduced is 20-40 Nm^3 per ton of polymer treated. The patent does not disclose an aliphatic hydrocarbon medium having 8 or more carbon atoms, it does not refer to oligomers, and it does not describe the polymer powder in the silo as constituting a fluid bed.

[0007] The U.S. Patent 5,047,446 to DeNicola discloses a method for the treatment of irradiated propylene polymer particles containing free radicals. In one embodiment the particles are treated by heating them in a bed of the particles fluidized by nitrogen or any other gas inert to the free radicals at $40-110^{\circ}\text{C}$ for 10 minutes-two hours. In another embodiment, they are then heated in a second fluid bed at $130-150^{\circ}\text{C}$ for at least about 20 minutes. The objective of the first step is to better control the recombination of the free radicals in the particles, while the objective of the second step is to better control the deactivation of residual free radicals. Nothing in this patent appears to suggest that the fluidizing gas from either bed contains oligomers.

[0008] This invention provides a non-melt method for stripping oligomers from finely divided, solid, substantially crystalline, α -olefin polymer particles containing such at a substantial concentration. The method consists essentially of:

establishing a bed comprising said particles at a temperature sufficient to evaporate oligomers from said particles,

but insufficient to cause said particles to become sticky to the extent they tend to substantially agglomerate and to adhere to walls;

fluidizing the bed by passing through said bed at a bed fluidizing velocity a stream of gas inert to the particles and oligomers under prevailing conditions, whereby evaporated oligomers are removed from the bed; and

maintaining said bed in its fluidized condition at such a temperature for a period of 1 hour to 3 hours sufficient for a substantial portion of said oligomers in said particles to evaporate therefrom and be removed from the bed, said temperature and period of time being selected according to the proportion and maximum length of the oligomers to be stripped from said particles.

[0009] One embodiment of the method is based on the discovery that in general the proportion and chain lengths of oligomers removed in the practice of the method are functions of temperature and residence time of polymer particles in the fluidized bed. It was found that the proportion of oligomers removed is a direct function of the residence time of the polymer particles in the fluidized bed. Further, it was found that the chain length of the oligomers removed is a direct function of the temperature of the polymer particles in the bed.

[0010] In this embodiment, the temperature and residence time of the polymer particles in the fluid bed are regulated so as to control both the proportion and the chain length of the oligomers removed from the particles, and thereby provide a polymer product with a residual content of oligomers, the concentration and chain lengths of which are necessary or desired in the use of the product in the manufacture of useful articles, or even in the articles themselves.

[0011] The polymer treated according to this invention is an α -olefin polymer that is normally solid and non-sticky in a range of practical temperatures, for example, 100-140°C, and that has a significant concentration of oligomers. Usually, such an α -olefin polymer has enough crystallinity to be solid and non-sticky up to an elevated temperature (a temperature substantially above 25°C), and to become molten at or above that temperature. As is well known, the temperature at which such a polymer becomes molten is referred to as the melting point. Examples of an α -olefin polymer with this crystallinity include such molding, film and fiber grade polymers as polyethylene, including high, medium and low density types; ethylene copolymers, including linear low density polyethylene and ultralow density polyethylene; polypropylene (propylene homopolymer); copolymers and terpolymers of propylene and other α -olefins such as ethylene and 1-butene, which terpolymers can include dienes, polybutenes and polystyrene; including blends of such polymers, which blends are made by sequential polymerization processes or by melt compounding methods.

[0012] The oligomer concentration of such α -olefin polymer can be in a broad range. A typical concentration is 1000-10,000 parts by weight per million parts by weight of the polymer, but higher and lower concentrations are within the broader scope of this invention. However, at an initial oligomer concentration below 250 parts by weight per million parts by weight of the polymer, the process is not very practical. One reason is that reducing concentration of oligomers below this level does not appear to have any useful effect.

[0013] According to this invention, the oligomers-bearing, α -olefin polymer to be treated is in the form of solid particles. The degree of oligomer reduction according to this invention does not appear to be significantly affected by particle size. Hence, the polymer particles can be of any practical size. However, in general, they are in a range of 5-200 mesh, (all particle sizes herein are U.S. screen sizes), and preferably, for operational reasons, they are in the range of 5-80 mesh.

[0014] Ways and means of establishing and maintaining a fluid bed of particles at a desired temperature, and introducing and withdrawing gas and particles to and from the bed are well known and need not be described here.

[0015] The fluidizing and stripping gas can be any gas that is inert to the polymer particles under the prevailing conditions, is a solvent for evaporated oligomers, and is not saturated with oligomers. Preferred examples of the gas are nitrogen, helium, argon and carbon dioxide. While oxygen and air can be used, in general they are to be avoided because of the risk of dust explosion. The gas preferably has little or no oligomers content when introduced into the bed. In most embodiments of the invention, for reason of economy, gas withdrawn from the bed is recycled. Usually it is treated to separate oligomer vapors therefrom. An example of such treatment is cooling the gas until oligomer vapors therein condense, and separating the condensed oligomers, usually in the form of an oil, from the gas. In these embodiments the gas, after separation of the condensed oligomers, is reintroduced into the bed, usually after it has been reheated to the temperature of the bed.

[0016] The temperature of the bed is established and maintained in a range, the upper end of which is dependent on the softening or sticky point of the polymer being treated. The lower end is dependent on the vapor pressures or boiling points of the oligomers to be removed from the polymer. For polypropylene the range is 100-140°C. For propylene-ethylene random copolymers in which the polymerized ethylene content is 2-5% by weight the range is 100-125°C.

[0017] The residence time of the polymer particles in the fluid bed is dependent on the porosity of the particles, the bed temperature, and the rate of migration at the bed temperature from the interstices of the particles to their surfaces

of the highest molecular weight oligomer to be removed therefrom. In general, for most oligomers-bearing, α -olefin polymers in the as-polymerized particles form commonly known as flake, the average particle size of which is about 60 mesh, and such polymers in the as-polymerized spherical particle form, the average particle size of which is about 10 mesh, the residence time is in the range from 1 hour to 3 hours for an optimal reduction of oligomers content.

[0018] One embodiment of the invention is based on the discovery that, by regulating the bed temperature and the residence time of the polymer particles in the bed, not only the proportion, but also the maximum chain length, of the oligomers stripped from the polymer particles can be significantly controlled. This is advantageous in those instances where a residual concentration of relatively higher molecular weight oligomers in the polymer particles can be tolerated, thus leading to energy savings, or is wanted because of the beneficial effect of such oligomers on the melt rheology of the polymer particles. In general, the higher the bed temperature the higher the chain length, and thus molecular weight, of the oligomers removed, while the longer the residence time, the greater is the proportion of the longer chain length oligomers that is stripped from the polymer particles. Further generalizations are not practical, because so much depends on the circumstances of specific situations. However, in view of the disclosures herein, the combinations of bed temperatures and residence times to obtain optimum concentrations and minimum chain lengths of residual oligomers in the treated polymer particles can be readily determined for each situation without undue experimentation.

[0019] The method of this invention can be practiced in batch mode or in continuous mode.

[0020] When the method is practiced in the batch mode, the polymer particles to be treated are introduced into a suitable, fluid bed vessel in sufficient quantity to form a static bed therein, the bed is fluidized with oligomer stripping gas, while withdrawing gas that leaves the bed, and the bed temperature is established in the oligomer removal range. The bed is maintained in the fluid state at a temperature in that range until the desired extent of oligomer removal has occurred. In one embodiment of the batch mode practice of the method, introduction of stripping gas into the bed is stopped, the particles either are allowed to cool to a temperature at which they can be handled, and removed from the vessel, or are removed from the vessel and allowed to cool to that temperature. In the more preferred embodiment, the bed is maintained in its fluid condition by the continued introduction of stripping gas into the bed, and withdrawal of gas that has left the bed, while the bed is cooled to a handling temperature, and at such temperature the introduction of stripping gas is stopped and the treated polymer particles are removed from the vessel.

[0021] In the continuous mode, a bed of polymer particles to be treated is formed in a suitable, fluid bed vessel, stripping gas is introduced continuously into the vessel at a velocity sufficient to fluidize the bed, the temperature of the bed is established and maintained in the treatment temperature range for that polymer, gas from the bed is continuously removed from the vessel, polymer particles to be treated are introduced continuously into one part or zone of the bed, and polymer particles are continuously removed from another part or zone of the bed. In this mode, the rates of introduction and withdrawal of polymer particles to and from the bed are selected to maintain the bed and to provide the desired average residence time of the particles in the bed.

[0022] Features of this invention are illustrated by the following Examples in which "ppm" means parts by weight per million parts by weight of the polymer, and all melt flow rates are per ASTM D 1238, Condition L.

Example 1

[0023] This Example illustrates the effects of bed temperature and residence time on reduction of the oligomers content of an α -olefin polymer.

[0024] The α -olefin polymer of this Example was a semi-crystalline polypropylene containing a conventional antioxidant at a conventional concentration. Its nominal melt flow rate was 30 dg/min. Its oligomer content by gas chromatographic analysis was 3220 ppm. The polymer was in the form of spherical particles having the following particle size distribution:

Particle Size (mesh)	Percent (by weight)
+5	1.1
-5/+10	51.5
-10/+14	37.2
-14/+35	10.2
-35/+140	0.0
-140	0.0

[0025] The fluid bed equipment comprised a 46cm by 46cm by 61cm, fluid-bed vessel with a sintered metal diffuser plate. In operative combination with the vessel was a closed loop, recirculating, nitrogen gas system with a gas blower, the name-plate blower speed of which was 1000 scfm, and an in-line fined-tube heat exchanger heated with hot oil. Two sources of hot oil were available, the hot oil of one source being at 80°C, the other being at 140°C. Each source was connected by a valved conduit to a manifold coupled to the heat exchanger so that either source could be selected to feed the heat exchanger.

[0026] 11.4 Kilograms of the polymer were introduced into the vessel, whereby a static bed was formed, and the bed was fluidized with nitrogen at 80°C for 120 minutes with samples of the thus treated polymer being withdrawn from the bed every 15 minutes. The gas temperature then was raised to 140°C, and the polymer particles in the fluid bed were treated for an additional 105 minutes, samples of the bed again being taken every 15 minutes. The quantity of nitrogen passed through the fluid bed during the additional 105 minutes was equivalent to 233,333 m³ per metric ton of polymer treated. Gas chromatographic analysis of the samples resulted in the data in the following Table.

TABLE I			
Residence Time in Minutes At 80°C	Oligomer Concentration (ppm)	Residence Time in Minutes at 140°C	Oligomer Concentration (ppm)
15	3210	15	3250
30	3370	30	3020
45	3130	45	2820
60	3095	60	2600
75	3200	75	2440
90	3080	90	2340
105	3350	105	1940
120	3300		

[0027] As can be seen, treatment of the polymer for 120 minutes 80°C did not significantly reduce its total oligomer concentration from the initial 3220 ppm. On the other hand, treatment at 105 minutes at 140°C reduced the oligomer concentration by 40% to 1940 ppm.

[0028] The following examples illustrate the effects of temperature and residence time not only on the reduction of the total oligomer content of the α -olefin polymer treated according to this invention, but also on the concentration and chain lengths of the residual oligomers in the polymers after treatment.

[0029] In these examples a laboratory size, fluidized bed system was used. A pipe with inside diameter of about 5 centimeters and length of about 0.9 meter, and a porous, sintered metal diffuser plate at its lower end, was the fluidized bed vessel. The vessel wall was temperature controlled with electrical heating tape to a tolerance of $\pm 3^\circ\text{C}$, and the

EP 0 735 053 B1

fluidization gas stream was preheated with a 1200 watt electric gas flow-through heater. The fluidization gas temperature was measured with a thermocouple placed about 5 centimeters upstream of the diffuser plate, and the gas temperature was controlled with a feedback controller. Gas flow rates were measured by a Rotometer upstream of the gas heater, and nominally set at 50 scfm for "flake" grade polymers, and at 200 scfm for the spherical particle polymers which had generally larger particle sizes. There was no gas recycle.

[0030] In each run of each of these Examples the fluidized bed vessel was charged with 300 grams of untreated polymer, and the resulting bed was fluidized. The fluidizing gas and oligomer stripper was nitrogen. The temperature at which the fluidized bed was established, and the period of time in which the bed was maintained at such temperature, are set forth in the following Tables. At the end of each run, after the treated polymer particles had cooled, the vessel was emptied, and a sample of the polymer particles was taken and analyzed by gas chromatography for total content of oligomers and, except for the 100°C runs, their carbon atom contents. The gas chromatographic analysis ("GCA") data thus obtained are reported in the following Tables. "nd" in the Tables means: not determined.

Example 2

[0031] The α -olefin polymer of this Example was a semi-crystalline polypropylene with a conventional antioxidant at a conventional concentration. Its nominal melt flow rate was 30 dg/min. The polymer was in the form of spherical particles having the following particle size distribution:

Particle Size (Mesh)	Percent (By Weight)
+5	1.1
-5/+10	51.5
-10/+14	37.2
-14/+35	10.2
-35/+140	0.0
-140	0.0

[0032] The GCA data obtained are in the following Table II.

TABLE II										
R. Time (min.)	Oligomers concentration (ppm) of polymer									
	Before Treat-ment	After Treatment At								
		100°C			120°C			140°C		
		2-1	2-2	2-3	2-4	2-5	2-6	2-7	2-8	2-9
0	2141									
30		1646			1812			957		
120			1293			1077			350	
180				1129			762			180
Carbons:	9-36	nd	nd	nd	15-36	18-36	21-36	12-36	24-36	27-36

Example 3

[0033] The α -olefin polymer here was a flake grade semi-crystalline polypropylene with a conventional antioxidant at a conventional concentration. Its nominal melt flow rate was 30 dg/min. The particle size distribution of the polymer

particles was:

Particle Size (mesh)	Percent (by weight)
+10	0.0
-10/+20	4.3
-20/+30	8.5
-30/+40	35.4
-40/+60	39.4
-60/+80	7.0
-80/+100	2.4
-100/+200	0.5
-200	2.5

[0034] The GCA data obtained are in Table III.

TABLE III										
R. Time (min.)	Oligomers concentration (ppm) of polymer									
	Before Treat- ment	After Treatment At								
		100°C			120°C			140°C		
		3-1	3-2	3-3	3-4	3-5	3-6	3-7	3-8	3-9
0	5171									
30		2524			3830			3664		
120			2112			2534			1277	
180				1927			2208			1378
Carbons:	9-36	nd	nd	nd	12-36	18-36	18-36	18-36	24-36	24-36

Example 4

[0035] In this Example the α -olefin polymer was a semi-crystalline polypropylene with a conventional antioxidant at a conventional concentration, and nominal melt flow rate of 440 dg/min. The polymer was in the form of spherical particles having the following particle size distribution:

Particle Size (mesh)	Percent (by weight)
+5	0.0
-5/+10	61.0
-10/+14	31.3
-14/+35	7.6
-35/+140	0.0
-140	0.1

[0036] Table IV reports the GCA data.

TABLE IV										
R. Time (min.)	Oligomers concentration (ppm) of polymer									
	Before Treat- ment	After Treatment At								
		100°C			120°C			140°C		
		4-1	4-2	4-3	4-4	4-5	4-6	4-7	4-8	4-9
0	5343									
30		5066			4614			3441		
120			3612			2474			1540	
180				3362			2135			1109
Carbons:	12-36	nd	nd	nd	15-36	18-36	18-36	18-36	24-36	27-36

Example 5

[0037] The α -olefin polymer in this Example was a semi-crystalline polypropylene with a conventional antioxidant at a conventional concentration. Its nominal melt flow rate was 70 dg/min. The polymer was in the form of spherical particles having this particle size distribution:

Particle Size (mesh)	Percent (by weight)
+5	0.0
-5/+10	25.3
-10/+14	44.4
-14/+35	29.1
-35/+140	0.3
-140	0.9

[0038] Table V reports the GCA data.

TABLE V										
R. Time (min.)	Oligomers concentration (ppm) of polymer									
	Before Treat- ment	After Treatment At								
		100°C			120°C			140°C		
		5-1	5-2	5-3	5-4	5-5	5-6	5-7	5-8	5-9
0	4627									
30		3655			2801			2669		
120			2591			1592			978	
180				2392			1289			952
Carbons:	9-36	nd	nd	nd	15-36	21-36	21-36	18-36	27-36	27-36

Example 6

[0039] In the runs of this Example the α -olefin polymer was a semi-crystalline polypropylene with a conventional antioxidant at a conventional concentration. Its nominal melt flow rate was 20 dg/min. The polymer particles were spherical and had this particle size distribution:

Particle Size (mesh)	Percent (by weight)
+5	0.0
-5/+10	27.3
-10/+14	40.8
-14/+35	31.0
-35/+140	0.1
-140.0	0.8

[0040] The GCA data that resulted are in Table VI.

TABLE VI										
R. Time (min.)	Oligomers concentration (ppm) of polymer									
	Before Treat- ment	After Treatment At								
		100°C			120°C			140°C		
		6-1	6-2	6-3	6-4	6-5	6-6	6-7	6-8	6-9
0	2338									
30		1283			1267			1143		
120			1065			946			441	
180				775			572			363
Carbons:	12-36	nd	nd	nd	21-36	24-36	27-36	24-36	27-36	30-36

Example 7

[0041] The α -olefin polymer in this Example was another flake grade, semi-crystalline polypropylene. It also contained a conventional antioxidant at a conventional concentration. The nominal melt flow rate of the polymer was 9.5 dg/min. The particle size distribution of the polymer particles was:

Particle Size (mesh)	Percent (by weight)
+10	0.0
-10/+20	8.1
-20/+30	11.5
-30/+40	36.1
-40/+60	33.6
-60/+80	5.9
-80/+100	2.0
-100/+200	0.2
-200	2.7

[0042] The GCA data obtained are in Table VII.

TABLE VII							
R. Time (min.)	Oligomers concentration (ppm) of polymer						
	Before Treat- ment	After Treatment At					
		120°C			140°		
		7-1	7-2	7-3	7-4	7-5	7-6
0	2646						
30		2105			1772		
120			1137			942	
180				1008			857
Carbons:	9-36	12-36	18-36	18-36	18-36	24-36	27-36

[0043] The foregoing data demonstrate that not only is the method of this invention effective in stripping oligomers from semi-crystalline, α -olefin polymer particles, but by regulation of temperatures and bed residence times, the extent of removal of oligomers can be controlled on the basis of their chain length or molecular weight. This is an advantage when retention of the higher molecular weight oligomers in the polymer is desired because of their beneficial effect on the melt rheological properties of the polymer.

Claims

1. A method of stripping oligomers from finely divided, substantially crystalline, α -olefin polymer particles containing oligomers at a significant concentration consisting essentially of:

establishing a bed comprising said particles at a temperature sufficient to evaporate oligomers from said particles, but insufficient to cause said particles to become sticky to the extent they tend to substantially agglomerate and to adhere to walls,

fluidizing said bed by passing through said bed at a bed fluidizing velocity a stream of gas inert to said particles and oligomers under prevailing conditions, whereby evaporated oligomers are removed from the bed, and

maintaining said particles at such a temperature for a period of 1 hour to 3 hours sufficient for a substantial portion of said oligomers in said particles to evaporate therefrom, said temperature and period of time being selected according to the proportion and maximum length of the oligomers to be stripped from said particles.

2. A method according to claim 1 in which the steps are carried out by introducing into one zone of the bed said polymer particles having oligomers at said significant concentration, and removing from another zone of the bed polymer particles with substantially reduced oligomers concentration.

3. A method according to claim 1 in which said gas is nitrogen.

4. A method according to claim 1 in which said polymer particles are semi-crystalline propylene polymer particles.

5. A method according to claim 4 in which said temperature is 100-140°C.

6. A method according to claim 1 in which the minimum chain length of the oligomers in the polymer particles to be treated by the method is nine carbon atoms.

7. A method according to claim 6 in which the minimum chain length of the oligomers in the polymer particles after treatment by the method is 18-36 carbon atoms.

Patentansprüche

1. Verfahren zum Abtrennen von Oligomeren aus feinteiligen, im wesentlichen kristallinen α -Olefinpolymerteilchen mit einem Gehalt an Oligomeren in einer signifikanten Konzentration, im wesentlichen bestehend aus:

Einrichten eines diese Teilchen umfassenden Bettes bei einer Temperatur, die zum Verdampfen von Oligomeren aus den Teilchen ausreicht, jedoch unzureichend ist, um zu verursachen, dass die Teilchen in dem Ausmaß klebrig werden, dass sie dazu neigen wesentlich zu agglomerieren und an den Wänden zu haften,

Fluidisieren des Bettes durch Hindurchleiten eines unter den vorherrschenden Bedingungen gegenüber den Teilchen und Oligomeren inerten Gasstroms mit einer das Bett fluidisierenden Geschwindigkeit, wodurch verdampfte Oligomere aus dem Bett entfernt werden,

Halten der Teilchen bei einer solchen Temperatur während eines Zeitraums von 1 Stunde bis 3 Stunden, die ausreicht, dass ein wesentlicher Teil der Oligomeren in den Teilchen hieraus verdampfen, wobei die Temperatur und der Zeitraum gemäß dem Anteil und der maximalen Länge der aus den Teilchen abzutrennenden Oligomeren ausgewählt werden.

2. Verfahren gemäß Anspruch 1, bei dem die Verfahrensstufen durch Einführen der Polymerteilchen mit Oligomeren in der signifikanten Konzentration in eine Zone des Fließbetts, und Entfernen von Polymerteilchen mit einer wesentlich verminderten Oligomerenkonzentration aus einer anderen Zone des Fließbetts durchgeführt werden.

3. Verfahren gemäß Anspruch 1, bei dem das Gas Stickstoff ist.

4. Verfahren gemäß Anspruch 1, bei dem die Polymerteilchen Teilchen aus semikristallinem Propylenpolymer sind.

5. Verfahren gemäß Anspruch 4, bei dem die Temperatur 100 bis 140°C ist.

6. Verfahren gemäß Anspruch 1, bei dem die minimale Kettenlänge der Oligomeren in den durch das Verfahren zu behandelnden Polymerteilchen 9 Kohlenstoffatome ist.

7. Verfahren gemäß Anspruch 6, bei dem die minimale Kettenlänge der Oligomeren in den Polymerteilchen nach der Behandlung durch das Verfahren 18 bis 36 Kohlenstoffatome ist.

5 Revendications

1. Procédé consistant à débarrasser des oligomères des particules de polymères d' α -oléfines essentiellement cristallines, finement divisées, contenant des oligomères en une concentration importante, comprenant essentiellement les étapes consistant à:

établir un lit comprenant lesdites particules à une température suffisante pour évaporer des oligomères desdites particules, mais insuffisante pour rendre lesdites particules collantes au point qu'elles manifestent une tendance à s'agglomérer de manière substantielle et à adhérer aux parois,

fluidifier ledit lit en faisant passer à travers ledit lit, à une vitesse de fluidification du lit, un courant de gaz inerte vis-à-vis desdites particules et vis-à-vis des oligomères dans les conditions en vigueur, si bien que les oligomères évaporés sont éliminés du lit, et

maintenir lesdites particules à une température, pendant un laps de temps de 1 heure à 3 heures, suffisante pour évaporer une portion importante desdits oligomères présents dans lesdites particules, ladite température et ledit laps de temps étant sélectionnés en fonction de la proportion et de la longueur maximale des oligomères à débarrasser desdites particules.

2. Procédé selon la revendication 1, dans lequel on effectue les étapes en introduisant dans une zone du lit, lesdites particules de polymères possédant des oligomères dans ladite concentration importante et en éliminant d'une autre zone du lit, des particules polymères possédant une concentration d'oligomères essentiellement réduite.

3. Procédé selon la revendication 1, dans lequel ledit gaz est l'azote.

4. Procédé selon la revendication 1, dans lequel lesdites particules polymères sont des particules polymères de propylène semi-cristallin.

5. Procédé selon la revendication 4, dans lequel ladite température s'élève de 100 à 140°C.

6. Procédé selon la revendication 1, dans lequel la longueur de chaîne minimale des oligomères dans les particules polymères à traiter par le procédé correspond à 9 atomes de carbone.

7. Procédé selon la revendication 6, dans lequel la longueur de chaîne minimale des oligomères dans les particules polymères après traitement par le procédé s'élève de 18 à 36 atomes de carbone.